

MK[®] 83


ED0701

Description

Chemical Name Dibenzoylmethane or 1,3-diphenyl-1,3-Propanedione

CAS Number 120-46-7

Chemical Structure

Chemical Formula C₁₅H₁₂O₂

Molecular Weight 224.26

Specification

Appearance	Pale, yellow crystalline solid
Assay	98% min
Bulk Density	0.8 g/cc
Heat Loss	0.2% max
Melting Point	76°C
Packing	Net 50kg /fiber drum

Application

MK 83 is used mainly as heat stabilizer for PVC or other vinyl polymers and copolymers.

MAKUANG CHEMICAL CO., LTD.

TEL: +886-4-2682-1189. FAX: +886-4-2682-1192.

Company Address: No.25, E. 2nd St., Youth Industrial Park, Dajia Town, Taichung County 43770, Taiwan (R.O.C.)

Web Site: <http://www.makuangchem.com>Email: service@makuangchem.com